

Reynoclad®



TECHNICAL DATA SHEET

Reynoclad® Pre-Painted Aluminum Sheets

TECHNICAL DATA SHEET

Reynoclad® Pre-Painted Aluminum Sheets

Reynoclad® coil-coated aluminum sheets are offered in 0.080", 0.063", 0.059", and 0.039" thickness.

PROPERTY	UNITS	0.080" ALUMINUM SHEET	0.063" ALUMINUM SHEET	0.059" ALUMINUM SHEET	0.039" ALUMINUM SHEET
THICKNESS	in	0.08	0.063	0.059	0.039
	mm	2.0	1.6	1.5	1.0
THICKNESS TOLERANCE	in	+/-0.003	+/-0.003	+/-0.003	+/-0.002
	mm	+/-0.08	+/-0.07	+/-0.07	+/-0.05
AVAILABLE WIDTH	in	62, 59, 51, 39	62, 59, 51, 39	62, 59, 51, 39	62, 59, 51, 39
	mm	1575, 1499, 1295, 991	1575, 1499, 1295, 991	1575, 1499, 1295, 991	1575, 1499, 1295, 991
WIDTH TOLERANCE	in	-0/+0.12	-0/+0.125	+/-0.12	-0/+0.12
	mm	-0/+3	-0/+3	+/-3	-0/+3
ALLOYS	N/A	3000 Series	3000 Series	3000 Series	3000 Series
ALLOWABLE BENDING STRESS	lb/in ²	11,500	11,500	11,500	11,500
	MPa	79.3	79.3	79.3	79.3
COEFF. OF EXPANSION	in/in/°F	1.16x10 ⁻⁵	1.16x10 ⁻⁵	1.16x10 ⁻⁵	1.16x10 ⁻⁵
	mm/mm/°C	2.1x10 ⁻⁵	2.1x10 ⁻⁵	2.1x10 ⁻⁵	2.1x10 ⁻⁵
STIFFNESS (EI) ASTM C393	lbf/in ² /in	431.3	208	172.7	49.9
	MPa-cm ² /m	118.15	59.43	49.35	14.59
FLEXURAL MODULUS ASTM C393 (E)	lbf/in ²	1.01x10 ⁷	1.01x10 ⁷	1.01x10 ⁷	1.01x10 ⁷
	MPa	6.95x10 ⁴	6.95x10 ⁴	6.95x10 ⁴	6.95x10 ⁴
FINISHES / PERFORMANCE	NA	Coil-coated Pretreatment with 2 or 3-coat Meets AAMA 2605 / 2604 / 2603	Coil-coated Pretreatment with 2 or 3-coat Meets AAMA 2605 / 2604 / 2603	Coil-coated Pretreatment with 2 or 3-coat Meets AAMA 2605 / 2604 / 2603	Coil-coated Pretreatment with 2 or 3-coat Meets AAMA 2605 / 2604 / 2603

Reynoclad® Pre-Painted Aluminum Sheets

Information contained herein or related hereto is intended only for evaluation by technically skilled persons, with any use thereof to be at their independent discretion and risk. Such information is believed to be reliable, but HAS shall have no responsibility or liability for results obtained or damages resulting from such use. HAS grants no license under, and shall have no responsibility or liability for infringement of, any patent or other proprietary right. Nothing in this document should be construed as a warranty or guarantee by HAS, and the only applicable warranties will be those set forth in HAS's acknowledgment or in any printed warranty documents issued by HAS. The foregoing may be waived or modified only in writing by an HAS officer.

Hoover Architectural Solutions, LLC
50 Industrial Boulevard
Eastman, Georgia 31023-4129

1.800.841.7774
HOOVERAS.COM

Laws and building and safety codes governing the design and use of Hoover Architectural Solutions, LLC's products, and specifically aluminum materials, vary widely. It is the responsibility of the owner, the architect, the general contractor, the installer and the fabricator/transformer, consistent with their roles, to determine the appropriate materials for a project in strict conformity to all applicable national, regional and local building codes and regulations. REYNOPLATE® AND REYNOCLAD® HAVE SUCCESSFULLY PASSED ASTM E84 AND ASTM E136 TESTS. ENSURE THE PRODUCT IS USED IN A SYSTEM THAT COMPLIES WITH ALL APPLICABLE REGULATIONS. ANY LABORATORY TESTING INFORMATION PROVIDED BY HOOVER ARCHITECTURAL SOLUTIONS, LLC APPLIES ONLY TO THE PARTICULAR PRODUCT OR ASSEMBLY TESTED AND DOES NOT NECESSARILY REPRESENT HOW PRODUCTS WILL ACTUALLY PERFORM IN USE. REPORTS AND TEST DATA CORRESPONDING TO A PARTICULAR TESTED PRODUCT SAMPLE OR ASSEMBLY ARE NOT A GUARANTEE THAT THE SAME PRODUCT OR ASSEMBLY WOULD ALWAYS ACHIEVE THE SAME TEST RESULT.

Slight variations in color, gloss and texture can occur between different paint production batches. Paint variations within a specific color, especially for mica and metallic colors, can and do occur that are visible to the human eye, but are within industry tolerances.

Form No. EC 99603-008